



Test Report

No.: EBO1505091-C279

Date: June 3, 2015

Page 1 of 3

XIONGXIAN JUREN PAPER AND PLASTIC PACKING CO., LTD.
HUTAI INDUSTRY PARK, BAODING CITY, HEBEI PROVINCE, CHINA

The following sample(s) was/were submitted and identified on behalf of the clients as:

PLASTIC PACKAGE BAG

EBO Job No. : EBO1505091-C279

Material : CPP

Date of Sample Received : May 28, 2015

Testing Period : May 28, 2015 To June 3, 2015

Test Requested : As specified for client, for compliance with the Food and Drug Administration Regulations for polypropylene used in contact with food.

Test Method : With reference to FDA 21 CFR 177.1520.

Test Results : Please refer to next page(s).

Conclusion : Based on the performed tests on submitted sample(s), the test results comply with the FDA Specifications for polypropylene used in contact with food for the food simulation solvent used.

Signed for and on behalf of

Kevin Yu



EBO assures objectivity and justness of the test, and fulfill the duty of confidentiality for applicant's information. Applicant should undertake responsibility for the authenticity of submitted sample and information. Unless otherwise stated the results shown in the report refer only to the sample(s) tested. EBO shall not have any economic and legal responsibility because the use of testing result, or direct and indirect losses, and all legal consequences because of the result. This report is invalid without signatures of approver and special seal for inspection of EBO, or it has been reproduced in full or part. This Report is issued by EBO subject to its General Conditions of Service. Any unauthorized alteration, forgery or falsification of the content is unlawful, offenders may be prosecuted to the fullest extent of the law.



Test Report

No.: EBO1505091-C279

Date: June 3, 2015

Page 2 of 3

Test Results:

ID for specimen 1 : EBO1505091-C279.001

Description for specimen 1 : Transparent plastic

FDA 21 CFR 177.1520

<u>Simulant Used</u>	<u>Result</u>	<u>Limit</u>
Density at 23°C, g / cm ³	0.899	0.880 – 0.913
Extractable fraction in n-hexane at reflux temperature, w/w %	5.2	6.4 max
Soluble fraction in xylene at 25°C, w/w %	2.0	9.8 max

EBO assures objectivity and justness of the test, and fulfill the duty of confidentiality for applicant's information. Applicant should undertake responsibility for the authenticity of submitted sample and information. Unless otherwise stated the results shown in the report refer only to the sample(s) tested. EBO shall not have any economic and legal responsibility because the use of testing result, or direct and indirect losses, and all legal consequences because of the result. This report is invalid without signatures of approver and special seal for inspection of EBO, or it has been reproduced in full or part. This Report is issued by EBO subject to its General Conditions of Service. Any unauthorized alteration, forgery or falsification of the content is unlawful, offenders may be prosecuted to the fullest extent of the law.



Test Report

No.: EBO1505091-C279

Date: June 3, 2015

Page 3 of 3

Sample photo:

No. EBO1505091-C279



EBO authenticate the photo on original report only

*** End of Report ***

EBO assures objectivity and justness of the test, and fulfill the duty of confidentiality for applicant's information. Applicant should undertake responsibility for the authenticity of submitted sample and information. Unless otherwise stated the results shown in the report refer only to the sample(s) tested. EBO shall not have any economic and legal responsibility because the use of testing result, or direct and indirect losses, and all legal consequences because of the result. This report is invalid without signatures of approver and special seal for inspection of EBO, or it has been reproduced in full or part. This Report is issued by EBO subject to its General Conditions of Service. Any unauthorized alteration, forgery or falsification of the content is unlawful, offenders may be prosecuted to the fullest extent of the law.